

ESTIMATING USAGE

The tables below are a guide for estimating the amount of material recommended, depending on the end use.

Coating Plywood/Hardwood		
For use with: SilverTip, General Purpose, Cold Cure, Clear Coat, and SB-112.		
Mixed resin/hardener coverage in square feet per gallon		
	Seal Coat	Build Coats
*Softwood	200-250	400/4 mils
Hardwood	250-300	400/4 mils
Vertical Surface	200-250	500/3 mils

*Some soft wood materials will require 2 seal coats due to higher absorption.

Fiberglassing		
For use with: SilverTip, General Purpose, Cold Cure, Clear Coat, and SB-112.		
Mixed resin/hardener coverage in square feet per gallon		
	Wet-Out	Fill Coats
4 oz. cloth	150	300
6 oz. cloth	130	250
10 oz. cloth	100	170
24 oz. Biaxial Tape	32	40

Adhesive Glue Lines			
For use with: G-2, Gel Magic, QuickCure 5 & 15, MetlWeld, and T-88.			
Mixed adhesive coverage in square feet per gallon			
	Thickness	Softwood	Hardwood
Clamped Joints	3-4 mils	400	500
Vacuum Bagging	8 mils	200	200
Stapled Veneer	20 mils	80	80

Filletts				
For use with: EZ-Fillet				
Fillet Size	1/4" X 1/4"	1/2" X 1/2"	3/4" X 3/4"	1" x 1"
Ounces Per Linear Foot	4	8	11	14

Fairing				
For use with: Quikfair				
Fairing Thickness	1/16"	1/8"	1/4 "	3/8"
Ounces Per Square Foot	5	10	20	30

U-TAH Cartridge*			
Bead Size	1/8" x 1/8"	1/4" x 1/4"	3/8" x 3/8"
T-88	44'	22'	11'
GelMagic	34'	17'	9'
Quick Cure 5 & 15	44'	22'	11'

*The units reflected are linear feet per cartridge.

System Three® Resins, Inc. P.O. Box 399, Auburn, WA 98071

The information contained herein is based on the data available to us and is believed to be correct. However, System Three Resins, Inc. makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. System Three assumes no responsibility for injury from the use of the product described herein.